

Production Plant

Crossville, TN 38555 US

238 Porcelain Tile Dr.

Stonepeak Ceramics, Inc. **Corporate Headquarters** 720 N Franklin St., Ste 500 Chicago, IL 60654 US

STONEPE K

TECHNCIAL DATA SHEET

1. PRODUCT NAME

Carrara Select 2.0 Marble Look Collection



Calacatta Renoire



Romano White



Romano Greige





Carrara Zebrino



2. PRODUCT DESCRIPTION









(Green Choice includes pre-consumer recycled materials and post-consumer recycled materials).

Stonepeak proudly contains factory and products certifications:







Size/Thickness:

24" x 48" x 5/16" (8 mm) nominal 12" x 24" x 5/16" (8 mm) nominal

Finishes:

Honed and Polished

Recommended Grout Joint:

3/32" or greater. All sizes modular with 3/16" grout joint (≈5 mm).


Grout joints of 1/8" inch or less, especially with larger format tiles or running bond patterns, may require floor flatness values more than the 1/4" in 10' (or 1/16" in 1.0') standard required by ANSI.

See ANSI A108.01 2.6.2.2.

For patterns with running bond/brick joints patterns Stonepeak recommends a maximum of 33% offset.

See ANSI A108.02 section 4.3.8.

Rev. July 29, 2024 Page_ 1



STONEPE K

Stonepeak Ceramics, Inc. **Corporate Headquarters** 720 N Franklin St., Ste 500 Chicago, IL 60654 US

Production Plant 238 Porcelain Tile Dr. Crossville, TN 38555 US

3. TECHNICAL DATA

Physical – Visual	ASTM TEST	Industry	Stonepeak
Properties		Standard	Results
Water absorption	C373	Impervious < 0.5%	≤ 0.1%
Thickness Dimension	C499	Range ± 0.04 Inc. Max.	≤ ± 0.04 Inc.
Facial Dimension	C499	± 0.25 %	≤ ± 0.25 %
Warpage average diagonal	C485	±0.40 %	≤ ± 0.40 %
Warpage average edge	C485	±0.40 %	≤ ± 0.40 %
Wedging	C502	± 0.25 %	≤ ± 0.25 %
Bond Strength	C482	≥ 50 psi	≥ 200 psi
Breaking Strength	C648	≥ 250 lbf	≥ 400 lbf
Hardness (Mohs)	Scratch Test (No regulated)	Range 0 - 10	≥7
Visible Abrasion Resistance for Glaze tiles	C1027	No Requirement, Range 0 - 5	Class 4
Frost Resistance	C1026	No sample must show alterations to surface	No evidence of Damage
Chemical Resistance	C650	No Requirement, Range E - A	Class A
Stain Resistance	C1378	No Requirement, Range E - A	Class A*
DCOF*	BOT 3000	≥ 0.42*	≥ 0.55*
Aesthetic Classification	Visual Evaluation Shade & texture	No Requirement, Range VO -V4	V2

^{*} All values given are for matte or honed material. No values are given for polished material. Stonepeak does not recommend polished surfaces in area subject to exposure from grease, oil or water.

For level interior spaces to be walked upon when wet (see ANSI A137.1 section 6.2.2.1.10 - Section 9.6 for test procedure).

INSTALLATION

All installation work using Stonepeak tiles will conform to the standards set forth in the latest version of ANSI A108/118 and/or the TCNA Handbook for Ceramic Tile installations.

Installation or setting materials:

Movement joints shall be provided throughout the tile and work will conform to ANSI Specification A108.01-3.7; A108.02 - 4.4. and TCNA Details EJ171.

Setting materials used will conform to the ANSI 118.4 standard or greater and be recommended by the selected manufacturer for the installation & setting materials for ceramic or porcelain tile based on the application requirements.

5. WARRANTY

Stonepeak guarantees that its products will be free of manufacturing defects, and they will meet or exceed the performance specifications set forth in ANSI 137.1.

6. MAINTENANCE

Care and Maintenance Recommendations Guide. Please refer to **Stonepeak Care and** Maintenance Recommendations Guide for all technical information as to the care of this collection.

7. TECHNICAL SERVICES

Technical Assistance:

Guide specifications, literature, SDS, tile samples, details and installation procedures are all available for your use at our libraries.

Please contact your nearest Stonepeak representative for merchandising.

Rev. July 29, 2024 Page_ 2