

PLANE DIMENSION

Porcelain tile classified as Impervious Group P1 is frost-resistant and chemically resistant. These characteristics are achieved through the dry-forming of high-quality mixtures composed of atomized and blended natural raw materials, such as kaolin minerals and feldspars.

Collection Description

| | |
|-------------------|--------------------|
| Company | Stonepeak Ceramics |
| Collection | Plane Dimension |
| Finishes | Feel Glint |
| Glazed/Unglazed | Glazed |
| Thickness in inch | 15/64 in |
| Thickness in mm | 6mm |
| Rectified | Yes |

Available Colors



Afyon Bianco



Calacatta Bluette

Nominal Sizes

Tile



60"x120"

PLANE DIMENSION

Product Dimensions (Rectified)

| Nominal Size (in) | Actual (in) | Nominal Size (cm) | Actual (mm) |
|-------------------|-------------------|-------------------|----------------------|
| 60 x 120 in | 59.06 x 118.19 in | 150 x 300 cm | 1500.00 x 3002.00 mm |

For more information about this collection scan below



Technical Features

| Physical Properties | Norms | Required Standards | Stonepeak Results ⁽¹⁾ |
|---------------------|-------------------------|--|--|
| Water Absorption | ASTM C 373 - 18 | Impervious ≤0.5% | ≤0.5% |
| Thickness Variation | ASTM C 499 - 20 | ± 0.02 inch | ± 0.02 inch |
| Facial Dimension | ASTM C 499 - 20 | ± 0.25 % | ± 0.25 % |
| Wedging | ASTM C 502 - 16 | ± 0.25 % | ± 0.25 % |
| Dry Bond Strength | ASTM C 482 - 20 | ≥ 150 psi | ≥ 150 psi |
| Breaking Strength | ASTM C 1505 - 20 | ≥ 175 lbf | ≥ 175 lbf |
| Modulus of Rupture | ASTM C 1505 - 20 | ≥ 6000 psi | ≥ 6000 psi |
| Deep Abrasion | ASTM C 1243 - 93 (2015) | ≥ 175mm ³ (0.011in ³) | ≥ 175mm ³ (0.011in ³) |
| Hardness (Mohs) | ASTM C 1895 - 20 | Range 0 - 10 | ≥ 7 ⁽²⁾ |
| Frost Resistance | ASTM C 1026 - 13 (2018) | No sample must show alterations to surface | No evidence of damage |
| Chemical Resistance | ASTM C 650 - 20 | Range A / E | Class A ⁽³⁾ |
| Stain Resistance | ASTM C 1378 - 20 | Range A / E | Class A ⁽³⁾ |
| Fire Resistance | ASTM E84 | Class A | Class A1-A1FL |

Result Notes


- (1) All values given are for textured/natural/structured finish. Values for different finishes are available upon request.
- (2) Mohs result referring to textured/natural finish. For polished/semi-polished/silky finish: ≥ 6.
- (3) Chemical and stain resistance refer to textured/natural finish. For polished/silky finish tests are provided on request. For more detailed information, refer to ANSI A137.1 Specifications for Ceramic Tile.

PLANE DIMENSION


Technical Features: Visual Evaluation Shade & Texture

Visual Evaluation


V1




V2



V3



V4




TCNA rates tile color and texture variation on a scale up to V4, with V4 indicating the highest variation.

This porcelain tile is rated V2, meaning moderate variation in tone, primarily consistent with slight differences between tiles.

Recommended Grout Joint

Recommended grout joint is 3/16" or greater.

Grout joints of 1/8" inch or less, especially with larger format tiles or running bond patterns, may require floor flatness values in excess of the 1/4" in 10' (or 1/16" in 1.0') standard required by ANSI.



For patterns with running bond/brick joints, Stonepeak recommends a maximum of 33% offset.

Technical Features: Recommended Use

Visible Abrasion Resistance ratings are based on ASTM C1027-19 testing, which measures surface wear under abrasive load, combined with our manufacturer-declared results.

Visible Abrasion Resistance data for this collection is available upon request.

Class 1

Residential Bathrooms

Class 2

All Residential Areas

Class 3

All Residential / Light Commercial

Class 4

All Residential / Commercial

Pre-Consumer Recycled Content

This porcelain product, manufactured at the Crossville, TN factory, contains at least **40% pre-consumer recycled content**, with all claims certified by Bureau Veritas Certification. Recycled content is a LEED metric intended to increase demand for building materials that incorporate reused or repurposed materials.



ISO 14021:2021 CONTENT OF RECYCLED MATERIAL
Rev.15 _ Issued 7.31.2024 Expired 9.03.2027

PLANE DIMENSION

Technical Features: DCOF - Wet Test

| Norm | Standard | Stonepeak Result ⁽⁴⁾ |
|---------------------|----------|---------------------------------|
| ANSI A 326.3 - 2021 | ≥0.42 | ≥0.42 + Feel, Glint |

Product Use Recommendation

| Finish | Classification | Criteria |
|-------------------|-------------------|-----------------|
| Natural, Polished | Interior Dry (ID) | ≥ 0.42 dry DCOF |
| Natural | Interior Wet (IW) | ≥ 0.42 wet DCOF |

More information can be found at: (<https://tcnatile.com/resource-center/dynamic-coefficient-of-friction/>)

Result Notes

- (4) DCOF results referring to textured/natural/structured products are performed with the WET test, while for polished, semi-polished and silky the DCOF test is performed DRY.
- (4) The DCOF values shown in the catalog, website, or other sales documents are for reference only and are non-binding. Any specific requirements must be confirmed by us at the time of order and, in any case, always prior to installation.
- (4) All values given are for textured/natural/structured finish.

Certifications, Memberships and Validations

Product Certifications and Validations



Organizational Memberships & Other Validations



More information

For more information regarding Product Care and Maintenance, Warranty and other technical documents refer to our Stonepeak Document Library: (www.stonepeakceramics.com/document-library/).

For more information scan below



Stonepeak Ceramics, Inc.
Corporate Headquarters
720 N Franklin St., Ste 500
Chicago, IL 60654 US

Production Plant
238 Porcelain Tile Dr.
Crossville, TN 38555 US

The technical data reported in this Technical Data Sheet are indicative and non-binding. The company reserves the right to make changes at any time without prior notice. Always refer to the latest available version of this document.